



## Anti-Graffiti Clear

1S122

# 4016 Gloss / 4018 Matte

A two-component topcoat clear with exceptional exterior durability and solvent resistance. Recommended as a protective topcoat over surfaces and substrates painted with catalyzed 1-Shot Background and Lettering Enamels that have been properly catalyzed with 1-Shot 4020 Hardener.



### Features & Benefits

- Excellent exterior durability
- Solvent resistant
- Most graffiti can be removed with solvent

### Required Additional Products

**Hardeners:** 4020 Hardener

### Directions For Use



#### Surface Preparation:

Apply over clean, dry surfaces that are free from wax, grease, dust, chalk, etc. and have been painted with 1-Shot Background and Lettering Enamels that have been properly cured with 4020 Hardener.



#### Mix Ratio:

Anti-Graffiti Clear	Hardener
1 Part	1 Part

- If thinning is required, use no more than 10% Acetone or MEK in the 4016 Gloss and no more than 20% in the 4018 Matte.
- Pot life of mixture is 2 hours at 72° F.



Matthews Paint • Toll Free: 800.323.6593 • Fax: 800.947.0377  
www.matthewspaint.com • www.1shot.com  
760 Pittsburgh Drive • Delaware, OH 43015

Product Information Effective 08/18  
Part No. 1S122 08/18  
© 2018 Matthews Paint Company

## Directions For Use (Continued)



### Application:

- Apply 1 thin coat.
- Flash 20 minutes between coats.
- Follow with a second full coat.
- Flash 30 minutes between additional coats.
- Apply a maximum of 3 full wet coats.
- Note: If waiting more than 60 minutes between coats, allow 6 hours to dry and lightly sand before proceeding with additional coats.



### Drying Times:

- Dry to touch: 2 hours
- Dry to handle: 4 hours
- Dry to graffiti removal/solvent resistant: 10 days

### 4016/4020 (Blended To Spray) Technical Data:

VOC Less Water Less Exempts.....	4.29 lbs./gal (514 g/L)
VOC Less Water Less Exempts - w/ 10% MEK.....	4.50 lbs./gal (539 g/L)
Solids by Weight (no MEK added).....	47.7%
Solids by Volume (no MEK added).....	40.0%
Theoretical Coverage (no MEK added).....	642 sq. ft./gal at 1 mil, 100% transfer efficiency

### 4018/4020 (Blended To Spray) Technical Data:

VOC Less Water Less Exempts.....	4.16 lbs./gal (498 g/L)
VOC Less Water Less Exempts - w/ 20% MEK.....	4.58 lbs./gal (549 g/L)
Solids by Weight (no MEK added).....	50.3%
Solids by Volume (no MEK added).....	41.5%
Theoretical Coverage (no MEK added).....	666 sq. ft./gal at 1 mil, 100% transfer efficiency

### Important:

The contents of this package may have to be blended with other components before the product can be used. Before opening the packages, be sure you understand the warning messages on the labels of all components, since the mixture will have the hazards of all its parts. Improper spray technique may result in a hazardous condition. Follow spray equipment manufacturer's instructions to prevent personal injury or fire. Follow directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

**See Material Safety Data Sheet and Labels for additional safety information and handling instructions.**

### Emergency Medical or Spill Control Information:

US (412) 434-4515; CANADA (514) 645-1320; Mexico 01-800-00-21-400

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public. Products mentioned may be hazardous and should only be used according to directions, while observing precautions and warning statements listed on label. Statements and methods described are based upon the best information and practices known to Matthews Paint. Procedures for applications mentioned are suggestions only and are not to be construed as representations or warranties as to performance, results, or fitness for any intended use, nor does Matthews Paint warrant freedom from patent infringement in the use of any formula or process set forth herein. If you require technical assistance, please call us toll-free 800/323-6593.