



**Acrylic Polyurethane Ultra Low VOC UV Free Clears**

MAP-UVF208/01 Gloss Clear  
 MAP-UVF228/01 Satin Clear  
 MAP-UVF238/01 Matte Clear

Matthews Acrylic Polyurethane Ultra Low VOC UV Free Clears are formulated specifically for clearcoating where fluorescent colors are used, such as amusement parks and dark ride attractions.

MAP-UVF clears are created without UV screeners, allowing fluorescent colors to glow while providing durable protection.



**Features:**

**Benefits:**

Durable yet flexible film .....Impact and mar resistant  
 Durable finish .....Adds depth and appearance  
 Air-dry or force-dry capable .....Fits most shop conditions  
 2K Acrylic polyurethane.....Long-term durability  
 Ultra low VOC technology .....Environmentally friendly; Complies with most stringent VOC requirements; High solids  
 Brush and roll capability.....For use in areas where air spraying is prohibited

**Compatible Surfaces:**

MAP-UVF Acrylic Polyurethane Ultra Low VOC UV Free Clears may be applied over properly prepared:

- MAP®
- Satin MAP®
- Satin VOC MAP®
- MAP-LVG Acrylic Polyurethane
- MAP-LVS Acrylic Polyurethane
- 74777SP/01 Tie Bond Adhesive
- 274777SP/01 Tie Bond Adhesive
- 274793SP/01 Spray Bond Adhesive

**Associated Products:**

**Catalyst**

MAP-LVX270/01\* Catalyst  
 \*Also available in /04

**Reducer**

MAP-LVRS01/01\* Cool Temp. Spray Reducer  
 MAP-LVRS02/01 Warm Temp. Spray Reducer w/ Extender  
 MAP-LVRS03/01 Hot Temperature Spray Reducer w/ Extender 80° & Above  
 MAP-LVRB51/01\* Brush and Roll Reducer

**Accelerator**

287437SP/08 HS Accelerator  
 MAP-LVA117/08 Ultra Low VOC Accelerator  
 47117SP/04 MAP Accelerator

# MAP-UVF Clears

## Directions for Use

**Surface Preparation:** Substrate should be prepared according to Matthews Substrate Preparation Guide prior to topcoat application.

**Mix Ratio:**



Mix Ratio for Spraying (by volume)

MAP-UVF Clears LVX270/01\* LVRS0x\*\* with Accelerator\*\*\*

3 parts                      1 part                      1 part                      Up to 1oz/RTS quart

- MAP-LVRS01/01\* Cool Temp. Spray Reducer
- MAP-LVRS02/01 Warm Temp. Spray Reducer with Extender
- MAP-LVRS03/01 Hot Temperature Spray Reducer with Extender 80° & Above
- NOTE: Larger jobs may require a hotter temperature reducer.
- For Brushing and Rolling, refer to Technical Data Sheet MPC193.
- All components should be mixed thoroughly before using
- Strain material after mixing

\*Also available in /04

\*\*Choose MAP reducer

\*\*\*Caution: use of accelerator with LVRS01/01\* is Not Recommended as it will drastically shorten pot life.



**Pot Life:** Pot-life is the amount of time before spray viscosity doubles. These are estimates based on lab results at 50% relative humidity, 70°F/21°C—results will vary based on application conditions, reducer selection, and accelerator choice.

Note: mix no more product than can be used within time limits listed below:

Application Method	Reducer	Accelerator*	Max load of accelerator per RTS qt	Pot-Life
Spraying	MAP-LVRS01/01*	Accelerator is Not Recommended when using MAP-LVRS01/01* reducer		1 hour
	MAP-LVRS02/01 or MAP-LVRS03/01	287437SP/08	1/2 oz	1.5 hours
		MAP-LVA117/08	1/2 oz	1 hour
		47117SP/04	1/2 oz	1 hour
Brush and Roll	LVRB51/01*	Accelerator is Not Recommended when brushing or rolling		1 hour

Times listed in the chart above are for a full load of accelerator.

\*Also available in /04

**Additives:**



None required, but the following may be used for specific application or project needs:

- 287112SP/04 Medium Suede Additive
- 287113SP/04 Coarse Suede Additive

**Spray Set Up:**



Air Pressure: Conventional: 40 - 50 psi at the gun\*

HVLP: 10 psi at the cap\*

\* Refer to spray gun manufacturer recommendations for inlet pressure.



Pressure Pot Fluid Delivery: 8 - 12 Fluid Ounces per Minute



Gun Set Up: Siphon Feed: 1.2 - 1.4 mm 0.047 - 0.055 fluid tip

HVLP: 1.2 - 1.4 mm 0.047 - 0.055 fluid tip

Pressure Pot: 1.0 - 1.2 mm 0.039 - 0.047 fluid tip

# MAP-UVF Clears

## Directions for Use

### Application:



Apply:

Apply two full wet coats, allowing proper flash time\* between coats. Apply additional coats as necessary to achieve total dry film thickness. \*Flash times will vary dependent upon film thickness, temperature, solvent selection, spray gun set-up, application, etc.

Recommended Film Thickness:

	Wet Film Thickness (WFT)	Per Coat	Total
		2 - 3 mils	4 - 6 mils
	Dry Film Thickness (DFT)	1 mils	2 mils

**Caution:** All 2-component crosslinking slows significantly at temperatures below 60°F or 16°C. Never spray or subject freshly painted coatings to these conditions or loss of gloss, decreased durability and improper curing can occur.

### Estimated Drying Times:



Air-Dry @ 50% Relative Humidity, 70°F/21°C  
MAP-UVF Clears (Mixed 3:1:1 with LVX270/01\* and Reducer)

Reducer	Accelerator*	Dust Free	Set to Touch	Dry to Handle	Tape Time	Vinyl Application (2-3 mils)	Reflective Metallic Vinyl Application
MAP-LVRS01/01*	Not recommended	10-15 minutes	25-35 minutes	45-60 minutes	1-2 hours	8-11 hours	16-22 hours
MAP-LVRS02/01 or MAP-LVRS03/01	287437SP/08	10-15 minutes	15-20 minutes	25-40 minutes	1-1½ hours	7-10 hours	12-16 hours
	MAP-LVA117/08	10-15 minutes	15-20 minutes	25-40 minutes	1-1½ hours	7-10 hours	12-16 hours
	47117SP/04	10-15 minutes	15-20 minutes	25-40 minutes	1-1½ hours	7-10 hours	12-16 hours

Times listed in the chart above are for a full load of accelerator.

\*Also available in /04

**Recoating:** Paint films cured over 24 hours should be cleaned, lightly dry scuff sanded with 320 – 400g by hand/machine or wet sanded with 600g, then cleaned again before recoating.

**Force Dry:** Allow 30 minute purge before baking to prevent solvent popping. Bake for 40 minutes at 140°.

### Equipment Cleaning:

Clean equipment promptly with any low VOC all-purpose cleaning solvent. Acetone should be used for cleanup in environmentally regulated areas.

**Note: Do not leave mixed material in equipment.**

### Technical Data:

#### VOC Information

VOC Actual RTS	0.18 – 1.85 lbs/gal
VOC Actual RTS	22 – 221 g/L
VOC Regulatory (less water less exempt) RTS	0.36 – 2.30 lbs/gal
VOC Regulatory (less water less exempt) RTS	43 – 276 g/L

For complete VOC information, visit [MatthewsPaint.com](http://MatthewsPaint.com) > Quick Links > VOC Data

#### Performance Characteristics

Volume solids (RTS)	45.28% - 54.88%
Theoretical Coverage (1 mil @ 100% transfer efficiency)	727 - 761 sq.ft./RTS gal
Application Conditions - Temperature	60°F (16°C) Minimum 100°F (38°C) Maximum
Application Conditions - Relative Humidity	85% maximum 5° above dew point

# MAP-UVF Clears

Acrylic Polyurethane  
Ultra Low VOC  
UV Free Clears

**Important:** The contents of this package may have to be blended with other components before the product can be used. Before opening the packages, be sure you understand the warning messages on the labels of all components, since the mixture will have the hazards of all its parts. Improper spray technique may result in a hazardous condition. Follow spray equipment manufacturer's instructions to prevent personal injury or fire. Follow directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

**See Safety Data Sheet and Labels for additional safety information and handling instructions.**

EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION - US (412) 434-4515; CANADA (514) 645-1320; Mexico 01-800-00-21-400  
Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public. Products mentioned may be hazardous and should only be used according to directions, while observing precautions and warning statements listed on label. Statements and methods described are based upon the best information and practices known to Matthews Paint. Procedures for applications mentioned are suggestions only and are not to be construed as representations or warranties as to performance, results, or fitness for any intended use, nor does Matthews Paint warrant freedom from patent infringement in the use of any formula or process set forth herein. If you require technical assistance, please call us toll-free 800/323-6593.



*The World's Finest Coating For Architectural Signage*

760 Pittsburgh Drive  
Delaware, OH 43015  
Toll Free: 800/323-6593  
Toll Free FAX: 800/947-0377